

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : A23G 3/30		A1	(11) International Publication Number: WO 96/20609
			(43) International Publication Date: 11 July 1996 (11.07.96)
(21) International Application Number: PCT/US95/13890		(81) Designated States: BR, CA, CN, CZ, HU, JP, KR, MX, PL, RU, SG, SK, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 27 October 1995 (27.10.95)			
(30) Priority Data: 08/365,650 29 December 1994 (29.12.94) US		Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	
(71) Applicant: WARNER-LAMBERT COMPANY (US/US): 201 Tabor Road, Morris Plains, NJ 07950 (US).		RECORD COPY CENTRAL FILE	
(72) Inventors: MANSUKHANI, Gul; 97 Petrus Avenue, Staten Island, NY 10312 (US). KIEFER, Jesse, J.; 2 High Rock Drive, Belvidere, NJ 07823 (US). D'OTTAVIO, Nick; 15 Petersburg Road, Hackettstown, NJ 07840 (US).			
(74) Agents: RYAN, M., Andrea; Warner-Lambert Company, 201 Tabor Road, Morris Plains, NJ 07950 (US) et al.			
(54) Title: NON-STICK CHEWING GUM			
(57) Abstract  A non-stick/chewing gum base composition which is free from fats, waxes, and elastomer solvent resins, and a non-stick chewing gum composition made from the gum base. The resulting chewing gum is easily removable from a variety of surfaces.			
<div style="text-align: center;"><div style="border: 1px solid black; border-radius: 50%; width: 60px; height: 60px; display: flex; align-items: center; justify-content: center; margin: 0 auto;"><div style="text-align: center;">5200 10</div></div><div style="display: flex; justify-content: space-around; margin-top: 10px;"><div style="text-align: center;">350 353 361 371 420 484 487 502 504 530 555</div><div style="text-align: center;">567 576 712 810</div></div></div>			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

5

**NON-STICK CHEWING GUM**

10

**BACKGROUND OF THE INVENTION****Field of the Invention**

15 The present invention concerns a non-stick chewing gum base composition which is free from fats, waxes, and elastomer plasticizing materials known as elastomer solvent resins, and a chewing gum composition prepared using the gum base.

20 **Description of the Background Art**

Chewing gums are conventionally prepared by adding sweeteners, flavoring agents and the like to a chewing gum base. Conventional gum bases normally contain, as a  
25 principal ingredient, any of a number of different resinous gum materials such as: (1) natural rubber elastomers (e.g., rubber latex, guayule, and the like); (2) natural gum elastomers (e.g., chicle, jelutong, balata, guttapercha, lechi caspi, sorva, pendare, perillo, leche de vaca, niger  
30 gutta, tunu, chiquibul, crown gum, and the like); (3) synthetic rubber elastomers (e.g., styrene-butadiene rubber, polyisobutylene, isobutylene-isoprene copolymers, polybutadiene, and the like); (4) hydrophobic synthetic polymers (e.g., polyvinyl acetates, ethylene/vinyl  
35 acetate, vinyl laurate/vinyl acetate copolymer, and the like); and (5) mixtures thereof. Other functional ingredients are typically present in conventional chewing gum bases to modify and tailor the overall properties of the resulting chewing gum, such as one or more of fats,  
40 waxes, elastomer solvent resins, fillers, softeners, emulsifiers, plasticizers, antioxidants, etc. The particular combination of ingredients used in a chewing gum base depends on factors such as the particular kind and

amount of resinous gum material employed and the overall desired texture and consistency characteristics of the resulting chewing gum composition (e.g., chew, stickiness, flavor release, springiness, film forming characteristic, elasticity, etc.).

Fats, waxes and elastomer solvent resins aid in softening and plasticizing the resinous gum material and also provide other desirable properties. For example, fats provide chewing gum smoothness, waxes improve the elasticity of its chew character, and elastomer solvent resins provide it with chew bulkiness. However, fats, waxes, and elastomer solvent resins also adversely affect the characteristics of the chewing gum; for example, they result in increased stickiness and reduced flavor release. For example, fats such as hydrogenated or partially hydrogenated vegetable oils including cottonseed and soybean oils, hydrogenated or partially hydrogenated animal fats, cocoa butter, and the like reduce the viscosity of the gum base, causing it to become sticky. Waxes such as paraffin wax, microcrystalline wax, petroleum wax, natural waxes, and the like also result in more stickiness. Elastomer solvent resins used as softeners and tackifiers for the resinous gum material, such as methyl, glycerol, or pentaerythritol esters of rosins or modified rosins, including hydrogenated, dimerized, or polymerized rosins, terpene resins including polyterpene and polymers of alpha-pinene or beta-pinene, and the like, also contribute to tackiness. As a result, conventional chewing gums have been criticized by some who believe that gums that have been consumed and improperly discarded pollute the environment by sticking to the surfaces on which they have been deposited.

Because conventional chewing gums adhere strongly to a variety of surfaces including wood, floors, asphalt pavement, concrete, carpet, leather, hair, and cloth, discarded chewing gums that are stuck to those surfaces are often difficult and costly to remove. Oftentimes, even after the chewing gums have been removed, stains are left

on the surfaces. As a result, vendors have been banned from selling conventional chewing gums to consumers in many public places such as train stations, arenas, amusement parks, and schools. The country of Singapore has flatly  
5 banned the selling of chewing gums. Accordingly, a chewing gum that is easily removable from the surfaces on which it is discarded or deposited would be highly desirable.

Conventional chewing gums that have non-stick  
10 characteristics are typically designed not to adhere to natural teeth and synthetic dental products during chewing. These chewing gums, however, still adhere to other surfaces when they are discarded. For example, U.S. Patent Nos. 3,984,574, 4,357,355, 4,518,615, and 5,266,336 disclose  
15 non-tack chewing gum compositions that do not adhere to dentures, fillings, or natural teeth, but none-the-less stick to other surfaces.

U.S. Patent Nos. 4,794,003 and 4,721,620 disclose bubble  
20 gum compositions that do not stick to the face. These compositions, however, contain waxes, fats, and elastomer solvent resins.

U.S. Patent No. 5,116,626 discloses a transparent gum base  
25 composition containing a variety of ingredients such as synthetic rubber elastomers, polyvinyl acetates, softeners, and fillers, and optionally fats, waxes, and elastomer solvent resins.

U.S. Patent No. 3,285,750 discloses a chewing gum  
30 composition that is said to have low adherence to various surfaces. However, that chewing gum composition must contain a resinous adhesion resistant agent in powder form.

35 SUMMARY OF THE INVENTION

The present invention provides a non-stick chewing gum base composition which is free from fats, waxes, and elastomer solvent resins, comprising:

(1) a blend of polyvinyl acetates having different molecular weights in an amount effective to provide good chew properties;

(2) an amount of a non-fat, non-wax and non-elastomer solvent resin plasticizer effective to provide chew bulkiness and softness; and

(3) an amount of a filler effective to provide flavor release and integrity.

10 The present invention further provides a non-stick chewing gum composition, substantially free from fats, waxes, and elastomer solvent resins, comprising:

(1) an amount of the non-stick gum base composition of the invention effective to provide good chew properties;

(2) an amount of a surfactant having hydrophobic-lipophobic balance greater than about 7 effective to provide softness;

(3) an amount of a flow control agent effective to provide flowability; and

(4) an amount of a plasticizer effective to provide texture and consistency.

#### DETAILED DESCRIPTION OF THE INVENTION

25

The present invention concerns a non-stick chewing gum base composition that is free from fats, waxes, and elastomer solvent resins and is easily removable from surfaces on which it is deposited. The invention further concerns a finished chewing gum composition prepared using the gum base. The chewing gum composition of this invention is easily removable from a variety of surfaces on which it is deposited including wood, floors, asphalt pavement, concrete, carpet, leather, hair, and cloth. Moreover, it has high perceived flavor-release characteristics and retains chewing characteristics comparable to those of conventional chewing gums. This chewing gum is, therefore, highly desirable and should have great consumer appeal.

The gum base composition according to the present invention contains a blend of polyvinyl acetates having different molecular weights. More specifically, the gum base composition contains a blend of at least two of the following polyvinyl acetates: a low molecular weight polyvinyl acetate, a medium molecular weight polyvinyl acetate, and a high molecular weight polyvinyl acetate. The amounts of the different molecular weight polyvinyl acetates present in the gum base composition should be effective to provide the finished chewing gum with the desired non-stickiness and chew properties, such as integrity, softness, chew bulkiness, film-forming characteristic, hydrophilic character, and flavor release. The total amount of polyvinyl acetate used in the gum base composition is usually from about 45% to about 92% by weight based on the total gum base composition. It is preferred to use an amount of polyvinyl acetate from about 60% to about 85%, especially about 75% by weight of the total gum base composition.

Typically, the low molecular weight polyvinyl acetate has a weight average molecular weight of from about 2,000 to about 14,000, and preferably from about 11,000 to about 13,000. The amount of the low molecular weight polyvinyl acetate used in the gum base composition is usually from about 39% to about 75%, preferably from about 40% to about 50%, and most preferably about 44%, by weight based on the total weight of the gum base composition.

The medium molecular weight polyvinyl acetate typically has a weight average molecular weight of from about 15,000 to 55,000, and preferably from about 45,000 to about 55,000. The medium molecular weight polyvinyl acetate is typically employed in the gum base composition in an amount of from about 5% to about 41%, preferably from about 20% to about 40%, and most preferably about 32%, by weight based on the total weight of the gum base composition.

The high molecular weight polyvinyl acetate typically has a

weight average molecular weight of from about 56,000 to about 500,000. The high molecular weight polyvinyl acetate is typically employed in the gum base composition in an amount of up to about 10%, and preferably up to about 5%.  
5 The weight average molecular weight may be determined by conventional methods such as by gel permeation chromatography.

10 Preferably, at least one other resinous gum material is employed in the gum base composition of this invention. The amount of such additional resinous gum material present should be effective to provide a finished chewing gum with the desired chew bulkiness, springiness, flavor release, film forming characteristic, and elasticity. Typically the  
15 additional resinous gum material is present in an amount of up to about 10%, and preferably from about 5% to about 10%, and most preferably about 8% by weight based on the total weight of the gum base composition. Examples of suitable additional resinous gum materials include synthetic rubber  
20 elastomers such as styrene-butadiene rubber, polyisobutylene, polyisobutylene-isoprene copolymers (butyl rubber), polybutadiene, and the like, natural rubber elastomers such as rubber latex, guayule, and the like, and natural gum elastomers such as chicle, jelutong, balata,  
25 guttapercha, lechi caspi, sorva, pendare, perillo, leche de vaca, niger gutta, tunu, chiquibul, crown gum, and the like, and mixtures thereof.

A non-fat, non-wax and non-elastomer solvent resin  
30 plasticizer is added to the gum base composition of the present invention. Examples of suitable plasticizers include glycerol triacetate, acetylated monoglyceride, and mixtures thereof. The preferred plasticizer employed in the present invention is glycerol triacetate. The amount  
35 of the plasticizer present should be effective to provide a finished chewing gum with the desired chew bulkiness and softness. Typically, the plasticizer is employed in an amount of from about 3% to about 15% in the gum base composition, preferably from about 4% to about 12%, and



most preferably about 7%, by weight based on the total weight of the gum base composition.

5 The gum base composition of this invention further contains a filler. Examples of suitable fillers include calcium carbonate, magnesium carbonate, alumina, talc, tricalcium phosphate, and synthetic and natural clay, and mixtures thereof. A preferred filler is calcium carbonate. The amount of the filler present should be effective to provide  
10 a finished chewing gum with the desired flavor release, integrity, and non-stickiness. Typically, the filler is employed in the gum base composition in an amount of up to about 30%, usually 5% to 30%, preferably from about 5% to about 20%, and most preferably about 10%, by weight based  
15 on the total weight of the gum base composition.

The manner in which the constituents of the gum base composition are blended is not critical and may be performed using standard techniques and equipment known to  
20 those skilled in the art. Typically, any additional resinous gum material, such as a rubber elastomer, is agitated in a mixing kettle until a homogeneous mixture is obtained. The filler is then blended into the mixture. The polyvinyl acetate components are then added to the  
25 mixture. It is preferred that the high molecular weight polyvinyl acetate is added and blended first followed by the medium and then the low molecular weight polyvinyl acetates. In this manner, uniform blending can be achieved without the creation of isolated pockets of polyvinyl  
30 acetate in the elastomer. If no additional resinous gum material is employed in the gum base composition the polyvinyl acetate is blended as described and the filler is then blended into the polyvinyl acetate. The remaining ingredients may then be added in bulk, incrementally, or  
35 stepwise while mixing until a homogeneous mass is obtained. The homogeneous mass is usually discharged into a pan and allowed to cool and thereafter the gum base composition is incorporated into a chewing gum composition.

The chewing gum composition according to the present invention will now be discussed in more detail. Preferably, the chewing gum composition is substantially free from fats, waxes, and elastomer solvent resins. A minor amount of fats, waxes, or elastomer solvent resins may be present so long as the non-sticky characteristics of the finished chewing gum are not unacceptably or adversely affected. Typically, the amount of any fats, waxes, or elastomer solvent resins present should not exceed about 1% by weight based on the total weight of the chewing gum composition.

The amount of the gum base composition of this invention present in the chewing gum composition should be effective to provide the finished chewing gum with the desired non-stickiness and good chew properties. Typically, the chewing gum composition contains the gum base composition of this invention in an amount of from about 10% to about 50%, preferably from about 15% to about 35%, and most preferably from about 22% to about 26%, by weight based on the total weight of the chewing gum composition.

The chewing gum composition further contains a surfactant. Suitable surfactants should have an hydrophobic-lipophobic balance (HLB) of greater than about 7. Examples of suitable surfactants include polyoxyethylene (20) sorbitan monoleate, polyoxyethylene (20) sorbitan monolaurate, polyoxyethylene (4) sorbitan monolaurate, polyoxyethylene (20) sorbitan monopalmitate, polyoxyethylene (20) sorbitan monostearate, polyoxyethylene (4) sorbitan monostearate, polyoxyethylene (20) sorbitan tristearate, polyoxyethylene (5) sorbitan monooleate, polyoxyethylene (20) sorbitan trioleate, sorbitan monolaurate, and the like. The amount of surfactant present should be effective to provide the finished chewing gum with the desired softness and non-stickiness. Typically, the surfactant is employed in the chewing gum composition in an amount of from about 0.5% to about 1.5% and preferably about 1.0%, by weight based on the total weight of the chewing gum composition.

A flow control agent is added to the chewing gum composition according to the present invention. The amount of the flow control agent present should be effective to provide the finished chewing gum with the desired flowability and non-stickiness. Preferably, the flowability of the finished chewing gum is such that when the finished chewing gum had been chewed and deposited on a surface, the chewing gum would retain substantially its shape. Typically, the flow control agent is present in an amount of from about 0.5% to about 1.5% and preferably from about 0.5% to about 1.0%, by weight based on the total weight of the chewing gum composition. Examples of suitable flow control agent include amorphous silica, fumed silica, precipitated alumina, natural and synthetic clays, talc, cellulose fiber, and mixtures thereof.

In addition to the plasticizer in the gum base composition, plasticizers, as well as emulsifiers, are typically employed in the chewing gum composition according to the present invention, in conventional amounts. These (additional) plasticizers and the emulsifiers are preferably non-fat, non-wax, and non-elastomer solvent resin materials. Plasticizers provide a variety of desirable textures and consistency properties such as chew bulkiness and softness to the finished chewing gum and emulsifiers aid in dispersing the immiscible components of the chewing gum composition into a single stable system. Examples of suitable (additional) plasticizers include glycerol triacetate, acetylated monoglyceride, and mixtures thereof. Typically, the (additional) plasticizer is employed in the chewing gum composition in an amount of from about 0.1% to about 0.8% by weight based on the total weight of the chewing gum composition. Preferably, when glycerol triacetate is used as the (additional) plasticizer, the amount employed is from about 0.15% to about 0.25% by weight. When acetylated monoglyceride is used as the (additional) plasticizer, the preferred amount is about 0.6% by weight. Examples of suitable emulsifiers include lecithin, glycerol, glycerol monooleate, lactic

esters of fatty acids, lactylated fatty acid esters of glycerol and propylene glycol, mono-, di-, and tri-stearylacetates, monoglyceride citrate, stearic acid, stearyl monoglyceridyl citrate, stearyl-2-lactylic acid, triacytyl glycerin, triethyl citrate, polyethylene glycol, and mixtures thereof. The preferred emulsifiers are lecithin and stearic acid. Typically, the emulsifier is employed in the chewing gum composition in an amount of up to about 2%, by weight based on the total weight of the chewing gum composition.

An effective amount of a softening agent may also be added to the chewing gum composition of the present invention. Examples of suitable softening agents include glycerin, high fructose corn syrup, corn syrup, sorbitol solution, hydrogenated starch hydrolysate, fully unsaturated vegetable oils such as non-hydrogenated cotton seed oil, and mixtures thereof. A preferred softening agent is anhydrous glycerin, such as the commercially available United States Pharmacopeia (USP) grade. Glycerin is a syrupy liquid with a sweet warm taste and has a sweetness of about 60% of that of cane sugar. Because glycerin is hygroscopic, it is important that the anhydrous glycerin be maintained under anhydrous conditions throughout the preparation of the chewing gum composition. The amount of softening agent employed in the chewing gum composition is up to about 20% and preferably from about 10% to about 15%, by weight based on the total weight of the chewing gum composition. When a fully unsaturated vegetable oil is employed as a softening agent, the amount of the oil present should not exceed about 1% by weight, based on the total weight of the chewing gum composition. When the amount of oil present exceeds about 1% by weight, the non-stick characteristics of the finished chewing gum may be adversely or unacceptably affected.

The chewing gum composition according to the present invention may contain an effective amount of at least one sweetener. The sweetener may comprise saccharide

sweeteners, sugar alcohols, or intense sweeteners, or mixtures thereof.

Examples of suitable saccharide sweeteners include  
5 monosaccharides, disaccharides, and polysaccharides such as  
xylose, ribose, glucose, mannose, galactose, fructose,  
levulose, dextrose, sucrose, maltose, partially hydrolyzed  
starch, corn syrup, and high fructose corn syrup. Examples  
of suitable sugar alcohols include sorbitol, xylitol,  
10 mannitol, maltitol, isomalt, and hydrogenated starch  
hydrolysate.

Examples of suitable intense sweeteners include (A) water-  
soluble naturally-occurring intense sweeteners such as  
15 dihydrochalcones, monellin, steviosides, glycyrrhizin,  
dihydroflavenol, and L-aminodicarboxylic acid aminoalkenoic  
acid ester amides, such as those disclosed in U.S. Patent  
No. 4,619,834, and mixtures thereof; (B) water-soluble  
artificial sweeteners including the soluble saccharin salts  
20 such as sodium or calcium saccharin salts, cyclamate salts,  
the sodium, ammonium or calcium salts of 3,4-dihydro-6-  
methyl-1,2,3-oxathiazine-4-one-2,2-dioxide, the potassium  
salt of 3,4-dihydro-6-methyl-1,2,3-oxathiazine-4-one-2,2-  
dioxide (Acesulfam-K), the free acid form of saccharin, and  
25 the like, and mixtures thereof; (C) dipeptide based  
sweeteners including L-aspartic acid derived sweeteners,  
such as L-aspartyl-L-phenylalanine methyl ester (Aspartame)  
and materials described in U.S. Patent No. 3,492,131, L-  
alphaaspartyl-N-(2,2,4,4-tetramethyl-3-thietanyl)-D-  
30 alaninamide hydrate (Alitame), methyl esters of L-aspartyl-  
L-phenyl-glycerine and L-aspartyl-L-2,5-dihydrophenyl-  
glycine, L-aspartyl-2,5-dihydro-L-phenylalanine, L-  
aspartyl-L-(1-cyclohexene)-alanine, and the like, and  
mixtures thereof; (D) water-soluble intense sweeteners  
35 derived from naturally-occurring water-soluble sweeteners,  
such as chlorinated derivatives of ordinary sugar  
(sucrose), e.g., chlorodeoxysugar derivatives such as  
derivatives of chlorodeoxysucrose or  
chlorodeoxygalactosucrose, known, for example, under the

product designation of Sucralose®; examples of chlorodeoxysucrose and chlorodeoxygalactosucrose derivatives include but are not limited to: 1-chloro-1'-deoxysucrose; 4-chloro-4-deoxy-alpha-D-galactopyranosyl-alpha-D-fructofuranoside, or 4-chloro-4-deoxygalactosucrose; 4-chloro-4-deoxy-alpha-D-galactopyranosyl-1-chloro-1-deoxy-beta-D-fructofuranoside, or 4,1'-dichloro-4,1'-dideoxygalactosucrose; 1',6'-dichloro-1',6'-dideoxysucrose; 4-chloro-4-deoxy-alpha-D-galactopyranosyl-1,6-dichloro-1,6-dideoxy-beta-D-fructofuranoside, or 4,1',6'-trichloro-4,1',6'-trideoxygalactosucrose; 4,6-dichloro-4,6-dideoxy-alpha-D-galactopyranosyl-6-chloro-6-deoxy-beta-D-fructofuranoside, or 4,6,6'-trichloro-4,6,6'-trideoxygalactosucrose; 6,1',6'-trichloro-6,1',6'-trideoxysucrose; 4,6-dichloro-4,6-dideoxy-alpha-D-galactopyranosyl-1,6-dichloro-1,6-dideoxy-beta-D-fructofuranoside, or 4,6,1',6'-tetrachloro-4,6,1',6'-tetraideoxygalactosucrose; and 4,6,1',6'-tetraideoxy-sucrose, and mixtures thereof; and (E) protein based intense sweeteners such as thaumococcus danielli (Thaumatococcus danianus).

The amount of sweetener employed in the chewing gum composition will vary with the sweetener selected for a particular chewing gum. Thus, for any given sweetener a sufficient amount of sweetener is used to provide the level of sweetness desired. The saccharide sweeteners and sugar alcohols described above are usually used in an amount of from about 1% to about 70% and preferably in an amount of from about 40% to about 50%, by weight based on the total weight of the chewing gum composition. The intense sweeteners described above are usually used in an amount of up to about 1%, preferably from about 0.05% to about 0.4%, by weight based on the total weight of the chewing gum composition.

A flavoring agent may also be added to the chewing gum composition according to the present invention, in conventional amounts. Examples of suitable flavoring

agents include any natural, artificial, or synthetic flavors such as spearmint oil; cinnamon oil; oil of wintergreen (methylsalicylate); peppermint oils; citrus oils including lemon, orange, lime and grapefruit; fruit essences including apple, pear, peach, grape, strawberry, raspberry, cherry, plum, pineapple, and apricot; and mixtures thereof. The amount of flavoring agent employed is normally a matter of preference subject to factors such as flavor type and strength desired. In general, the chewing gum composition may contain from about 0.5% to about 3.0% by weight of the flavoring agent based on the total weight of the chewing gum composition. Other ingredients such as antioxidants and colorants may also be added to the chewing gum composition.

The chewing gum according to the present invention can be prepared by conventional methods. Generally, the gum base composition is added to a gum kettle in molten form, other ingredients such as the sweeteners, surfactants, plasticizers, flow control agents, softening agents, and flavoring agents are then added to the gum kettle, and mixed until a homogeneous mass is produced. The homogeneous mass is then fed into a rolling and scoring machine where the gum is rolled and scored to proper dimensions. The chewing gum may also be produced by a continuous process such as that described in U.S. Patent No. 5,045,325, the disclosure of which is hereby incorporated by reference.

The present invention will now be illustrated by the following non-limiting Examples.

#### EXAMPLE 1

A gum base composition was prepared with the following ingredients:

	<u>INGREDIENTS</u>	<u>PERCENT BY WEIGHT</u>
	Butyl Rubber <sup>1</sup>	2.00
	Polyisobutylene <sup>2</sup>	6.00
5	Polyvinyl Acetate (MW = 12,800)	43.75
	Polyvinyl Acetate (MW = 47,000)	31.50
	Glycerol Triacetate	6.75
	Calcium Carbonate	10.00
10	1. Polyisobutylene-isoprene copolymer having a weight average molecular weight of 400,000.	
	2. Polyisobutylene having a weight average molecular weight of 42,600 to 46,100.	
15	Butyl rubber was added to a mixing kettle that had been preheated for 1 hour to a temperature of about 115° to 120°C using steam under a pressure of 30 psi and then masticated for about 1 hour. The rubber broke into small	
20	pieces and was then softened with steam heat and mechanical action on the kettle. One third portion of the polyisobutylene was then added to the kettle and mixed for about 10 to 15 minutes until the mixture became homogeneous. Another one third portion of the	
25	polyisobutylene was then added to the kettle and mixed for 10 to 15 minutes until the mixture became homogeneous. The remaining one third portion was then added to the kettle and mixed for 30 to 45 minutes until the whole mixture became homogeneous and had a consistent texture. The	
30	mixture was then discharged into the pan and allowed to cool to room temperature.	
	The mixture was then added to the mixing kettle, which had again been preheated for 1 hour to a temperature of 110 to	
35	120°C using steam under a pressure of 30 psi, and mixed for 10 to 15 minutes. Calcium carbonate was then added to the kettle and mixed for 10 to 15 minutes until a homogeneous mixture was obtained. Polyvinyl acetate having a molecular weight of 47,000 was then added to the kettle and mixed for	
40	about 20 to 25 minutes until it was softened and blended into the homogeneous mixture. Polyvinyl acetate having a molecular weight of 12,800 was then added to the kettle and mixed for 20 to 25 minutes until the mixture became smooth. The steam was then shut off. Glycerol triacetate was then	



slowly added to the kettle in 10 to 15 minutes. The homogeneous mixture was then discharged into the pan and allowed to cool to room temperature from the discharge temperature of 105° to 110°C to obtain a gum base composition.

## EXAMPLES 2-4

Gum base compositions were prepared with the following ingredients:

PERCENT BY WEIGHT			
Ingredients	Example 2	Example 3	Example 4
Butyl Rubber	-	-	2.00
Polyisobutylene	6.00	-	-
Styrene-butadiene Rubber	2.00	8.00	6.00
Polyvinyl Acetate (MW=12,800)	43.75	43.75	43.75
Polyvinyl Acetate (MW=47,000)	31.50	31.50	31.50
Glycerol Triacetate	6.75	6.75	6.75
Calcium Carbonate	10.00	10.00	10.00

The gum base compositions were prepared in the same manner as in Example 1, except that in Examples 2 and 3, styrene-butadiene rubber was added to the preheated mixing kettle instead of butyl rubber, in Examples 3 and 4, polyisobutylene was not added, and in Example 3, styrene-butadiene rubber and butyl rubber were added together to the preheated mixing kettle.

## EXAMPLE 5

A non-stick chewing gum was prepared with the following  
5 ingredients:

	<u>INGREDIENTS</u>	<u>PERCENT BY WEIGHT</u>
10	Gum Base from Example 1	26.000
	Glycerol Triacetate	0.250
	Lecithin	0.500
	Crystalline Sorbitol	40.780
	Mannitol	15.000
15	Glycerin	12.000
	Peppermint Flavors	1.800
	Aspartame	0.170
	Encapsulated Aspartame	1.000
	Amorphous Silica	1.000
20	Polyoxyethylene (20)	1.000
	Sorbitan Monooleate	
	Non-Hydrogenated Cotton Seed Oil	0.500

The gum base from Example 1 was melted at a temperature of  
25 80° to 85°C. The molten gum base was then poured into a  
mixing kettle. Lecithin, polyoxyethylene (20) sorbitan  
monooleate, non-hydrogenated cotton seed oil, and glycerol  
triacetate were then added to the kettle and mixed for 1 to  
2 minutes. 2/3 crystalline sorbitol, mannitol, and  
30 amorphous silica were then added to the kettle and mixed  
for 2 minutes. The mixture was held for 1 minute and then  
glycerin was added while mixing the mixture. The remaining  
1/3 crystalline sorbitol was then added and mixed for 2  
minutes. While mixing, the peppermint flavors were added.  
35 The aspartame sweeteners were then added and mixed for 3  
minutes. The gum mixture was then discharged to a pan at  
temperature of 43 to 46°C. The gum was then rolled and  
scored to the proper dimensions on a Rolling and Scoring  
Machine.

40 The adhesive characteristics of the chewing gum thus  
produced were tested in two experiments. In the first  
experiment, the chewing gum was first chewed for about 15  
minutes and was then pressed on various surfaces, i.e.,  
45 floor tile, concrete, and hairs. Thereafter, it was

removed from those surfaces. The removals were observed by 3 investigators. The results showed that the chewing gum was 100% removable from those surfaces with little or no effort.

5

In the second experiment, samples of concrete were placed into a Fisher Iso-Temp forced draft oven at selected temperatures of 30, 40, 50, 60, and 70°C. As the concrete samples reached the desired temperatures, chewing gum that

10 had been chewed for about 15 minutes was pressed on the concrete samples and kept at those temperatures for two days to simulate the effects of exposure to a warm environment. The chewing gum was then removed from the concrete samples while under the observation of 3  
15 investigators. The results showed that the chewing gum was 100% removable with little or no effort up to 60°C. At 70°C, approximately 10% of the chewing gum remained on the concrete surface.

20 Various organoleptic attributes of the non-stick chewing gum prepared from Example 5 that had been stored for about 4½ weeks were evaluated by fifty people (25 men, 25 women). The results based on a hedonic liking scale of from 1 (disliked extremely) to 9 (liked extremely) are shown  
25 below:

ATTRIBUTES	RESULTS
Overall Liking	4.48
Initial Flavor Liking	5.34
30 Later Flavor Liking	4.58
Initial Cooling Mouthfeel	5.30
Later Cooling Mouthfeel	4.88
Initial Chew Texture Liking	3.82
Later Chew Texture Liking	4.82
35 Sweetness Liking	5.16
Long Lasting Flavor	5.66

## EXAMPLES 6-8

Non-stick chewing gums were prepared with the following ingredients:

Ingredients	PERCENT BY WEIGHT		
	Example 6	Example 7	Example 8
Gum Base from Example 2	25.000	-	-
Gum Base from Example 3	-	25.000	-
Gum Base from Example 4	-	-	25.000
Glycerol Triacetate	0.150	0.150	0.150
Lecithin	0.700	0.700	0.700
Peppermint Flavors	1.400	1.400	1.400
Glycerin	11.000	11.000	11.000
Mannitol	15.000	15.000	15.000
Crystalline Sorbitol	42.830	42.830	42.830
Aspartame	0.170	0.170	0.170
Encapsulated Aspartame	0.600	0.600	0.600
Stearic Acid	1.000	1.000	1.000
Sorbitan Monolaurate	1.000	1.000	1.000
Precipitated Silica	0.500	0.500	0.500
Non-Hydrogenated Cotton Seed Oil	0.650	0.650	0.650

The non-stick chewing gums were prepared in the same manner as in Example 5, except for substituting the different gum bases, surfactant, and flow control agent. In addition  
5 stearic acid was added in Examples 6 to 8 and mixed with the molten gum base.

The adhesive characteristics of the chewing gums prepared from Example 6 to 8 were tested by first chewing the  
10 chewing gums for about 15 minutes and pressing the chewed gums against carpet and concrete surfaces at room temperature. Thereafter, the pressed chewing gums were removed from those surfaces. The removal was observed by 3  
15 investigators. The results showed that the chewing gums were 100% removable from those surfaces with little or no effort.

While the present invention has been described with respect to what is presently considered to be the preferred  
20 embodiments, it is to be understood that the invention is not limited to the disclosed embodiments. The present invention is intended to cover various modifications and equivalent formulations included within the spirit and scope of the appended claims.

WHAT IS CLAIMED IS:

1. A non-stick chewing gum base composition which is free from fats, waxes, and elastomer solvent resins, comprising:
  - (1) a blend of polyvinyl acetates having different molecular weights in an amount effective to provide good chew properties;
  - (2) an amount of a non-fat, non-wax and non-elastomer solvent resin plasticizer effective to provide chew bulkiness and softness; and
  - (3) an amount of a filler effective to provide flavor release and integrity.
2. The non-stick gum base composition according to Claim 1, wherein said blend of polyvinyl acetates comprises at least two of a low molecular weight polyvinyl acetate, a medium molecular weight polyvinyl acetate, and a high molecular weight polyvinyl acetate.
3. The non-stick gum base composition according to Claim 2, comprising:
  - (1) from about 39% to about 75% by weight of said low molecular weight polyvinyl acetate;
  - (2) from about 5% to about 41% by weight of said medium molecular weight polyvinyl acetate;
  - (3) up to about 10% by weight of said high molecular weight polyvinyl acetate;
  - (4) from about 3% to about 15% by weight of said non-fat, non-wax, and non-elastomer solvent resin plasticizer; and
  - (5) from about 5% to about 30% by weight of said filler;wherein said percentages by weight are based on the total weight of the gum base composition.
4. The non-stick gum base composition according to Claim 1, further comprising at least one other resinous gum material.

5. The non-stick gum base composition according to Claim 4, wherein said composition contains from about 5% to 10% by weight of said at least one other resinous gum material.

6. The non-stick gum base composition according to Claim 4, wherein said at least one other resinous gum material is selected from the group consisting of synthetic rubber elastomers, natural rubber elastomers, natural gum elastomers, and mixtures thereof.

7. The non-stick gum base composition according to Claim 1, wherein said plasticizer is glycerol triacetate.

8. The non-stick gum base composition according to Claim 1, wherein said filler is calcium carbonate.

9. The non-stick gum base composition according to Claim 2, wherein said low molecular weight polyvinyl acetate has a weight average molecular weight of from about 2,000 to about 14,000.

10. The non-stick gum base composition according to Claim 2, wherein said medium molecular weight polyvinyl acetate has a weight average molecular weight of from about 15,000 to about 55,000.

11. The non-stick gum base composition according to Claim 2, wherein said high molecular weight polyvinyl acetate has a weight average molecular weight of from about 56,000 to about 500,000.

12. The non-stick gum base composition according to Claim 3, comprising (1) about 44% by weight of said low molecular weight polyvinyl acetate, (2) about 32% by weight of said medium molecular weight polyvinyl acetate, (3) about 8% by weight of said another resinous gum material, (4) about 7% by weight of said plasticizer, and (5) about 10% by weight of said filler.

13. A non-stick chewing gum composition substantially free from fats, waxes, and elastomer solvent resins, comprising:

- (1) an amount of the non-stick gum base composition of Claim 1 effective to provide good chew properties;
- (2) an amount of a surfactant having a hydrophobic-lipophobic balance greater than about 7 effective to provide softness;
- (3) an amount of a flow control agent effective to provide flowability; and
- (4) an amount of a plasticizer effective to provide texture and consistency.

14. A non-stick chewing gum composition according to Claim 13, comprising:

- (1) from about 10% to about 50% by weight of said gum base composition;
- (2) from about 0.5% to about 1.5% by weight of said surfactant;
- (3) from about 0.5% to about 1.5% by weight of said flow control agent; and
- (4) from about 0.1% to about 0.8% by weight of said plasticizer;

wherein said percentages by weight are based on the total weight of the chewing gum composition.

15. The non-stick chewing gum composition according to Claim 13, wherein said surfactant is polyoxyethylene (20) sorbitan monooleate or sorbitan monolaurate.

16. The non-stick chewing gum composition according to Claim 13, wherein said flow control agent is selected from the group consisting of amorphous silica, fumed silica, precipitated silica, natural and synthetic clays, talc, cellulose fiber, and mixtures thereof.

17. The non-stick chewing gum composition according to Claim 13, wherein said plasticizer is glycerol triacetate, acetylated monoglyceride, or mixtures thereof.



18. The non-stick chewing gum composition according to Claim 13, further comprising a sweetener.

19. The non-stick chewing gum composition according to Claim 18, wherein said sweetener comprises a saccharide sweetener.

20. The non-stick chewing gum composition according to Claim 18, wherein said sweetener comprises a sugar alcohol.

21. The non-stick chewing gum composition according to Claim 20, wherein said sugar alcohol comprises a mixture of sorbitol and mannitol.

22. The non-stick chewing gum composition according to Claim 18, wherein said sweetener comprises an intense sweetener.

23. The non-stick chewing gum composition according to Claim 13, further comprising at least one emulsifier.

24. The non-stick chewing gum composition according to Claim 23, wherein said emulsifier is lecithin, stearic acid, or mixtures thereof.

25. The non-stick chewing gum composition according to Claim 13, further comprising up to 20% by weight of at least one softening agent.

26. The non-stick chewing gum composition according to Claim 25, wherein said softening agent is glycerin.

27. The non-stick chewing gum composition according to Claim 26, wherein said softening agent is a fully unsaturated vegetable oil.

## INTERNATIONAL SEARCH REPORT

International Application No

PC/US 95/13890

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A23G3/30

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A23G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,5 116 626 (SYNOSKY ET AL.) 26 May 1992 cited in the application see claim 1; table I ---	1,2,7-11
A	EP,A,0 242 325 (WARNER LAMBERT) 21 October 1987 see the whole document ---	1-3
A	EP,A,0 271 445 (WARNER LAMBERT) 15 June 1988 see the whole document ---	1-3
A	WO,A,90 04926 (WM. WRIGLEY JR. COMPANY) 17 May 1990 see claims ---	13
-/-		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "B" document member of the same patent family

Date of the actual completion of the international search

22 April 1996

Date of mailing of the international search report

- 6. 05. 96

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

Lepretre, F

# INTERNATIONAL SEARCH REPORT

Int'l Patent Application No  
PLT/US 95/13890

## C (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>WO,A,93 17574 (WM. WRIGLEY JR. COMPANY) 16 September 1993</p> <p>-----</p>	

1

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/13890

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5116626	26-05-92	NONE	
EP-A-242325	21-10-87	US-A- 4721620	26-01-88
		AU-B- 576984	08-09-88
		AU-B- 7078987	15-10-87
		CA-A- 1299427	28-04-92
		DE-A- 3776712	26-03-92
		HK-A- 25695	03-03-95
		JP-C- 1831759	29-03-94
		JP-B- 3071098	12-11-91
		JP-A- 62236447	16-10-87
		US-A- 4794003	27-12-88
		ZA-A- 8701815	02-09-87
EP-A-271445	15-06-88	US-A- 4872884	10-10-89
		AU-B- 606097	31-01-91
		AU-B- 8139087	16-06-88
		CA-A- 1316749	27-04-93
		ES-T- 2053584	01-08-94
		HK-A- 147995	22-09-95
		JP-A- 63214147	06-09-88
		US-A- 4915958	10-04-90
		US-A- 4980178	25-12-90
		US-A- 4980177	25-12-90
		US-A- 5087460	11-02-92
		US-A- 5023093	11-06-91
		ZA-A- 8708846	26-05-88
WO-A-9004926	17-05-90	AU-B- 626939	13-08-92
		AU-B- 4500389	28-05-90
		CA-A- 1332533	18-10-94
		DE-D- 68915163	09-06-94
		DE-T- 68915163	01-12-94
		EP-A- 0407498	16-01-91
		FI-B- 96476	29-03-96
		JP-T- 3502166	23-05-91
WO-A-9317574	16-09-93	WO-A- 9317570	16-09-93
		US-A- 5286500	15-02-94
		US-A- 5342631	30-08-94

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PLI/US 95/13890

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9317574		US-A- 5286501	15-02-94
		US-A- 5336509	09-08-94
		CA-A- 2130568	16-09-93
		CA-A- 2130569	16-09-93
		CA-A- 2130570	16-09-93
		CA-A- 2130571	16-09-93
		CA-A- 2130572	16-09-93
		CA-A- 2130573	16-09-93
		CA-A- 2130574	16-09-93
		CA-A- 2130575	16-09-93
		CA-A- 2130576	16-09-93
		CN-A- 1075851	08-09-93
		EP-A- 0651612	10-05-95
		EP-A- 0652712	17-05-95
		EP-A- 0627885	14-12-94
		EP-A- 0633729	18-01-95
		EP-A- 0627886	14-12-94
		EP-A- 0661926	12-07-95
		EP-A- 0632695	11-01-95
		EP-A- 0632696	11-01-95
		EP-A- 0633730	18-01-95
		FI-A- 943824	19-10-94
		FI-A- 943825	20-10-94
		FI-A- 943826	20-10-94
		FI-A- 943827	20-10-94
		FI-A- 943828	20-10-94
		FI-A- 943829	26-10-94
		FI-A- 943830	26-10-94
		FI-A- 943831	26-10-94
		JP-T- 7506962	03-08-95
		WO-A- 9317571	16-09-93
		WO-A- 9317572	16-09-93
		WO-A- 9317573	16-09-93
		WO-A- 9317575	16-09-93
		WO-A- 9317576	16-09-93
		WO-A- 9317577	16-09-93
		WO-A- 9317578	16-09-93
		WO-A- 9317579	16-09-93
		WO-A- 9317580	16-09-93
		US-A- 5437877	01-08-95

### Information on patient family members

PLT/US 95/13890

From PCT/ISA/218 (patent family annex) (July 1992)

## PATENTS SUMMARY

11/06/98

Page 1

Country : Patent Cooperation Treaty (PCT)

Patent #: 96-020609 A

Index#: 5200

Inventor: Gul Mansukhani et al.

Issue Date: 07/11/96

Assignee: Warner-Lambert Company

Date of Application: 12/29/94

Title:

NON-STICK CHEWING GUM

Desc.:

A non-stick chewing gum base composition which is free from fats, waxes and elastomer solvent resins and a non-stick chewing gum made from the gum base are claimed. The base contains a blend of polyvinyl acetate resins having different molecular weights to provide good chew properties, a non-fat, non-wax, non-elastomer solvent resin plasticizer for chew bulkiness and softness and filler for flavor release and integrity. The chewing gum is easily removed from a variety of surfaces on which it may be deposited.

Key Words:

10 CHEWING GUM

350 GUM BASE

353 Synthetic Rubbers

361 Fillers

371 Softeners/Plasticizers

480 Silica

484 Surfactants

487 Polymers

502 Base Manufacture/Preparation

504 Mixing/Gum Manufacture

530 Chewing Gum Removal

555 Fast or Slow Release/Long Lasting

567 Chew Texture

576 Non-sticking

712 Warner-Lambert/American Chicle

810 Patent Cooperation Treaty (PCT)